

**NASA  
Technical  
Memorandum**

NASA TM - 100383

**COMPARISON OF TWO COMPUTER CODES  
FOR CRACK GROWTH ANALYSIS —  
NASCRAC VERSUS NASA/FLAGRO**

**PART ONE**

By R. Stallworth, C.A. Meyers, and H.C. Stinson

Structures and Dynamics Laboratory  
Science and Engineering Directorate

December 1989

(NASA-TM-100383) COMPARISON OF TWO COMPUTER  
CODES FOR CRACK GROWTH ANALYSIS: NASCRAC  
VERSUS NASA/FLAGRO (NASA) 28 p CSCL 20K

N90-25360

Unclass  
G3/39 0264763



National Aeronautics and  
Space Administration

George C. Marshall Space Flight Center

11



# Report Documentation Page

1. Report No. <b>NASA TM-100383</b>		2. Government Accession No.		3. Recipient's Catalog No.	
4. Title and Subtitle  <b>Comparison of Two Computer Codes for Crack Growth Analysis — NASCRAC Versus NASA/FLAGRO</b>				5. Report Date  <b>December 1989</b>	
				6. Performing Organization Code	
7. Author(s)  <b>R. Stallworth, C.A. Meyers, and H.C. Stinson</b>				8. Performing Organization Report No.	
				10. Work Unit No.	
9. Performing Organization Name and Address  <b>George C. Marshall Space Flight Center Marshall Space Flight Center, Alabama 35812</b>				11. Contract or Grant No.	
				13. Type of Report and Period Covered  <b>Technical Memorandum</b>	
12. Sponsoring Agency Name and Address  <b>National Aeronautics and Space Administration Washington, D.C. 20546</b>				14. Sponsoring Agency Code	
15. Supplementary Notes  <b>Prepared by Structures and Dynamics Laboratory, Science and Engineering Directorate.</b>					
16. Abstract  <p>This report presents results from the comparison study of two computer codes for crack growth analysis — NASCRAC and NASA/FLAGRO. The two computer codes gave compatible conservative results when the part through crack analysis solutions were analyzed versus experimental test data. Results showed good correlation between the codes for the through crack at a lug solution. For the through crack at a lug solution, NASA/FLAGRO gave the most conservative results.</p>					
17. Key Words (Suggested by Author(s))  <b>Critical Stress Intensity, Closure, Modified Forman Equation, Walker Equation, Safe Life</b>			18. Distribution Statement  <b>Unclassified — Unlimited</b>		
19. Security Classif. (of this report)  <b>Unclassified</b>		20. Security Classif. (of this page)  <b>Unclassified</b>		21. No. of pages  <b>26</b>	
				22. Price  <b>NTIS</b>	

## PREPARATION OF THE REPORT DOCUMENTATION PAGE

The last page of a report facing the third cover is the Report Documentation Page, RDP. Information presented on this page is used in announcing and cataloging reports as well as preparing the cover and title page. Thus it is important that the information be correct. Instructions for filling in each block of the form are as follows:

Block 1. Report No. NASA report series number, if preassigned.

Block 2. Government Accession No. Leave blank.

Block 3. Recipient's Catalog No. Reserved for use by each report recipient.

Block 4. Title and Subtitle. Typed in caps and lower case with dash or period separating subtitle from title.

Block 5. Report Date. Approximate month and year the report will be published.

Block 6. Performing Organization Code. Leave blank.

Block 7. Author(s). Provide full names exactly as they are to appear on the title page. If applicable, the word editor should follow a name.

Block 8. Performing Organization Report No. NASA installation report control number and, if desired, the non-NASA performing organization report control number.

Block 9. Performing Organization Name and Address. Provide affiliation (NASA program office, NASA installation, or contractor name) of authors.

Block 10. Work Unit No. Provide Research and Technology Objectives and Plans (RTOP) number.

Block 11. Contract or Grant No. Provide when applicable.

Block 12. Sponsoring Agency Name and Address. National Aeronautics and Space Administration, Washington, D.C. 20546-0001. If contractor report, add NASA installation or HQ program office.

Block 13. Type of Report and Period Covered. NASA formal report series; for Contractor Report also list type (interim, final) and period covered when applicable.

Block 14. Sponsoring Agency Code. Leave blank.

Block 15. Supplementary Notes. Information not included elsewhere: affiliation of authors if additional space is re-

quired for block 9, notice of work sponsored by another agency, monitor of contract, information about supplements (film, data tapes, etc.), meeting site and date for presented papers, journal to which an article has been submitted, note of a report made from a thesis, appendix by author other than shown in block 7.

Block 16. Abstract. The abstract should be informative rather than descriptive and should state the objectives of the investigation, the methods employed (e.g., simulation, experiment, or remote sensing), the results obtained, and the conclusions reached.

Block 17. Key Words. Identifying words or phrases to be used in cataloging the report.

Block 18. Distribution Statement. Indicate whether report is available to public or not. If not to be controlled, use "Unclassified-Unlimited." If controlled availability is required, list the category approved on the Document Availability Authorization Form (see NHB 2200.2, Form FF427). Also specify subject category (see "Table of Contents" in a current issue of STAR), in which report is to be distributed.

Block 19. Security Classification (of this report). Self-explanatory.

Block 20. Security Classification (of this page). Self-explanatory.

Block 21. No. of Pages. Count front matter pages beginning with iii, text pages including internal blank pages, and the RDP, but not the title page or the back of the title page.

Block 22. Price Code. If block 18 shows "Unclassified-Unlimited," provide the NTIS price code (see "NTIS Price Schedules" in a current issue of STAR) and at the bottom of the form add either "For sale by the National Technical Information Service, Springfield, VA 22161-2171" or "For sale by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402-0001," whichever is appropriate.

## TABLE OF CONTENTS

	Page
NASA/FLAGRO SAFE LIFE FEATURES.....	2
NASCRAC SAFE LIFE FEATURES.....	3
ANALYSIS NOTES .....	4
COMPARISON ANALYSIS CHART.....	5
OBSERVATIONS.....	22
REFERENCES.....	23



## TECHNICAL MEMORANDUM

### COMPARISON OF TWO COMPUTER CODES FOR CRACK GROWTH ANALYSIS — NASCRAC VERSUS NASA/FLAGRO

The structural integrity of space flight hardware is established by a combination of qualification tests and analyses which simulate actual operating conditions, including flight loads, temperatures, and corrosive environments. These structural analysis and test activities usually fall into three distinct areas. The first two areas, strength and fatigue analysis, assume the load carrying structure is unflawed. This assumption implies that no defects have been introduced during the manufacturing process of each individual part, which in reality can never be possible on an economical basis.

The existence of flaws is accounted for in the third area, fracture mechanics. This area becomes an important effort in which defects are known as a result of quality inspections, or assumed to exist in a part and an assessment is made as to their impact on the parts useful life. Fracture mechanics attempts to predict the useful service life of an initially flawed structural part by calculating crack growth and eventual part failure due to unstable crack growth.

This paper compares the service life calculations of two computer codes, NASCRAC and NASA/FLAGRO. The analysis technique is based on linear elastic fracture mechanics (LEFM), in which stresses remain below the yield strength of an elastic/plastic material. Subcritical crack growth calculations assume that in a metallic part, the extent of yielding at the crack tip is very small compared to the crack size, uncracked ligament, and the bulk of the cracked body remains elastic.

To perform service life calculations, one must have a relationship expressing incremental crack growth,  $DA/DN$ , as a function of loading, geometry, and crack size. Load, crack size, and geometry are expressed in terms of the cyclic stress intensity factor,  $\Delta K$ . The crack growth rate as a function of  $\Delta K$  is then determined by material tests, plotting  $DA/DN$  versus  $\Delta K$  for the given material form and H.T. condition, loading condition, and environment.

Crack growth rate equations such as the Paris, Walker, and modified Forman equations are used to obtain a "best fit" curve to the laboratory  $DA/DN$  versus  $\Delta K$  data. Constants in the equations which result in a "best fit" then become crack growth rate material constants for a particular set of laboratory conditions.

Two extreme values of  $\Delta K$  also become material constants;  $\Delta K_0$  is the threshold stress intensity below which no crack growth occurs,  $K_c$  is the critical stress intensity at which a crack becomes unstable and complete fracture occurs. Formulations of  $\Delta K$  solutions and crack growth rate equations form the basis of computer codes which numerically integrated the  $DA/DN = F(\Delta K)$  relationship.

Before a computer code is used as part of the structural integrity assessment process, it should be exercised thoroughly and its numerical calculations checked to insure reasonable and accurate answers. The results presented herein compare the Safe Life calculations of two computer codes with each other, and with test data to a limited extent.

The computer program NASA/FLAGRO (commonly known as NASGRO) became available in 1986 from the NASA Johnson Space Center. The program was developed under the guidance of the NASA Fracture Control Analytical Methodology Panel and contains stress intensity factor solutions to a number of commonly used crack geometries. Service life calculations are performed with the modified Forman equation which reduces to the Walker or Paris equation depending on material constants used.

NASA/FLAGRO is menu driven and prompts the user for information in a serial manner. After selecting the type of analysis desired, such as Safe Life, the user answers a series of questions and enters data depending on the particular path taken. Generally, the program operates serially, requiring the user to follow the same path and answer a number of basic questions before each execution.

The computer program NASCRAC is being developed by Failure Analysis Associates under contract to NASA at Marshall Space Flight Center. For Safe Life analysis, NASCRAC has basically the same capabilities as NASA/FLAGRO, although implemented differently. Generally, stress intensity factors are obtained from influence function solutions to various geometries for which exact solutions do not exist. NASCRAC enables the user to select any one of several commonly used crack growth equations; including the Paris, Walker, and modified Forman equations.

NASCRAC is similar to NASA/FLAGRO in that the program is menu driven and the user answers questions and enters data in response to screen prompts. With NASCRAC, however, the user is not required to answer a series of questions before each execution. The user may randomly select only those menu items relating to the particular solution desired.

## NASA/FLAGRO SAFE LIFE FEATURES

NASA/FLAGRO features which can affect Safe Life calculation:

- (1) For surface cracks with constant amplitude loading,  $\Delta K$  is multiplied by a crack closure factor  $\beta_R$ .

$$\beta_R = \begin{cases} 0.9 + 0.2 R^2 - 0.1 R^4 & ; R > 0 \\ 0.9 & ; R \leq 0 \end{cases}$$

This can increase fatigue life.

- (2)  $\Delta K_{th}$ , the fatigue threshold is calculated using,

$$\Delta K_{th} = (1 - C_o R)^d \Delta K_o$$



To be conservative, let  $C_o = d = 1$  for  $R \geq 0$

$$\Delta K_{th} = (1-R) \Delta K_o$$

For small cracks,  $a \leq 0.025$  in,  $\Delta K_o = 0$ .

(3) Input of

$K_{IC}$  – plane strain fracture toughness

$K_{Ie}$  – fracture toughness for an elliptical crack

$A_k, B_k$  – fit parameters

To calculate  $K_C$  – critical stress intensity,

$$a) t_o = 2.5 \left( \frac{K_{IC}}{\sigma_{ys}} \right)^2$$

$$b) w = \left( \frac{A_k t}{t_o} \right)^2$$

$$c) K_C = K_{IC} (1 + B_k e^{-w})$$

$K_C$  is incorporated into the modified Forman equation to accelerate  $DA/DN$  as  $K_c$  is approached.

### **NASCRAC SAFE LIFE FEATURES**

(1) Crack growth equations

- |                    |                                       |
|--------------------|---------------------------------------|
| a) Modified Forman | Analytical Comparison                 |
| b) Walker          | Comparison to test data on both codes |

(2) Piecewise Linear Approximation method used.

(3) K-solutions are based on influence functions with the default order of accuracy.

## ANALYSIS NOTES

### Surface Flaws

NASCRAC — Uses  $K_{Ic}$  value to accelerate DA/DN per the Forman equation and defines failure when  $\Delta K > K_{Ic}$ , where  $K_{Ic}$  is manually input.

NASA/FLAGRO — Uses  $K_c$  value calculated from  $K_{Ic}$  and other variables to accelerate DA/DN per the Forman equation when  $\Delta K > K_{Ic}$ , where  $K_{Ic}$  is a material constant for surface flaws.

### Growth Rate Equations

NASCRAC — Uses the following growth equations: Paris, Modified Forman, Walker, Collipriest, and Hop Rau.

NASA/FLAGRO — Primarily uses the Modified Forman Equation but the Paris and Walker equations could be used.

### $K_c$ Values

NASCRAC —  $K_c$  is used in the Modified Forman equation but  $K$  is the controlling cutoff value.

NASA/FLAGRO — For  $B_k \neq 0$ , NASA/FLAGRO uses a  $K_{Ic}$  larger than  $K_{Ic}$  for thin material (Reference 8)

$$K_c/K_{Ic} = 1 - B_k e^{-w}$$

when  $B_k = 0$ ,  $K_c = K_{Ic}$ , where  $w = (A_k t/t_0)^2$ .

## COMPARISON ANALYSIS CHART

Type of Geometry	Parameters	Type of Run	NASGRO	NASCRAC
Through Center Crack	W = 10.0	*R = 0 Tension Only	X	X
	t = 0.25			
	4130 Steel	*R = -1 Tension Only	X	X
	a <sub>i</sub> = 0.05			
	σ <sub>t</sub> = 50 Ksi	Closure	X	X
	No Closure	X	X	
Through Edge Crack	W = 10.0	*R = 0 Tension Only	X	X
	t = 0.25			
	4130 Steel	*R = -1 Tension Only	X	X
	σ <sub>t</sub> = 50 Ksi			
	σ <sub>b</sub> = 50 Ksi	Closure	X	X
	a <sub>i</sub> = 0.05	No Closure	X	X
		*R = 0 Bending Only	X	X
		*R = - 1 Bending Only	X	X
		Closure		
		No Closure	X	X
		*R = +0.5 Tension	X	X
		Closure		
		No Closure	X	X
		*R = - 0.5 Tension	X	X
		Closure		
		No Closure	X	X
		R = +0.5 Bending	X	X
		Closure		
		No Closure	X	X
	R = -0.5 Bending	X	X	
	Closure			
	No Closure	X	X	
	a = 0.25	R = 0 Tension	X	X
		R = -1 Tension	X	X
		Closure		
		No Closure	X	X


\*See analysis results.

<u>Type of Geometry</u>	<u>Parameters</u>	<u>Type of Run</u>	<u>NASGRO</u>	<u>NASCRAC</u>
Through Crack at Pin Loaded Hole	$W = 1.75$ $t = 0.44$ $D = 0.375$ $B = 0.83$ 4340 Steel $\sigma_t = 59 \text{ Ksi}$ $\sigma_b = 37 \text{ Ksi}$ $a = 0.25$	*R = 0 Tension + Bearing	X	X
Through Crack at Pin Loaded Lug	$W = 5.0$ $t = 0.25$ $D = 0.5$ $\sigma_t = 150 \text{ Ksi}$ 4130 Steel $a_i = 0.05$ $a_i = 0.10$ $a_i = 0.25$	$R = 0$ $R = 0$ *R = 0	X X X	X X X
Surface Flaw Center Crack Specimen	Test Spec. No. 62* $W = 4$ $t = 0.50$ $\sigma_t = 84 \text{ Ksi}$ $a_i = 0.06$ $a_i/2c_i = 1/2$ Ti = 6AL-4V	R = +0.05	X	X
	Test Spec. No. 5576* $W = 4$ $t = 0.50$ $\sigma_t = 57 \text{ Ksi}$ $a_i = 0.06$ $a_i/2c_i = 1/2$ Ph-13-8M <sub>o</sub>	R = +0.05	X	X

\*See analysis results.

# GEOMETRY MODELS


**NASGRO**



$$S_1 = \frac{6M}{Wt^2}$$


**THROUGH CENTER CRACK**

**NASCRAC**




**202**

**TC01**



**TC02**


**THROUGH EDGE CRACK**



**sigma\_zz**

**203**

**S0 + P/Wt**




**S0**

$$S_1 = P/Dt$$

**TC03**


**THROUGH CRACK AT HOLE PIN LOADED**



**sigma\_zz**

**208**

**NASGRO**




$$S_0 = P/Dt$$


**TC04**

**THROUGH CRACK  
AT LUG**

**NASCRAC**




**209**




$$S_1 = \frac{6M}{Wt^2}$$

**SC01**


**SURFACE CRACK  
(CENTER)**




**702**



# ANALYSIS RESULTS THROUGH CENTER CRACK



$w = 10''$   
 $t = 0.25''$   
 $2a_i = 0.05''$   
 4130 STEEL  
 $\sigma = 50\text{KSI}$   
 1)  $R = 0$   
 2)  $R = 1$



NASGRO MODEL TYPE TC01

NASCRAC MODEL TYPE 202

## FIRST CASE $R=0$

NASGRO

$K_{MAX} = 80.10 \text{ KSI} \sqrt{\text{IN}}$  @ 20,173 CYCLES  $2a = 1.584''$

NASCRAC

$K_{MAX} = 80 \text{ KSI} \sqrt{\text{IN}}$  @ 20,176 CYCLES  $2a = 1.60''$

## SECOND CASE $R=-1$


NASGRO

CLOSURE:  $K_{MAX} = 80.12 \text{ KSI} \sqrt{\text{IN}}$  @ 16,401 CYCLES  $2a = 1.584''$   
 NO CLOSURE:  $K_{MAX} = 80.04 \text{ KSI} \sqrt{\text{IN}}$  @ 4,459 CYCLES  $2a = 1.58''$

NASCRAC

CLOSURE:  $K_{MAX} = 80 \text{ KSI} \sqrt{\text{IN}}$  @ 4433 CYCLES  $2a = 1.60''$   
 NO CLOSURE: SAME AS CLOSURE

# THROUGH EDGE CRACK



NASGRO MODEL TYPE TC02 NASCRAC MODEL TYPE 203

## TENSION ONLY

### FIRST CASE $R = 0$

NASGRO

$$K_{MAX} = 80 \text{ KSI } \sqrt{\text{IN}} \text{ @ 9674 CYCLES } a_f = 0.610"$$

NASCRAC

$$K_{MAX} = 83.22 \text{ KSI } \sqrt{\text{IN}} \text{ @ 9616 CYCLES } a_f = 0.655"$$

### SECOND CASE $R = -1$

NASGRO

CLOSURE:  $K_{MAX} = 80 \text{ KSI } \sqrt{\text{IN}} \text{ @ 7901 CYCLES } a_f = 0.61"$

NO CLOSURE:  $K_{MAX} = 80 \text{ KSI } \sqrt{\text{IN}} \text{ @ 2148 CYCLES } a_f = 0.61"$

NASCRAC

CLOSURE:  $K_{MAX} = 83.20 \text{ KSI } \sqrt{\text{IN}} \text{ @ 4439 CYCLES } a_f = 0.655$

NO CLOSURE: SAME AS CLOSURE



## THROUGH EDGE CRACK TENSION CASES CONTINUED

### THIRD CASE R=+0.5

#### NASGRO

CLOSURE  $K_{MAX}=80.05 \text{ KSI} \sqrt{\text{IN}}$  @ 27,485 CYCLES  $a=0.61''$   
NO CLOSURE  $K_{MAX}=80.05 \text{ KSI} \sqrt{\text{IN}}$  @ 43,772 CYCLES  $a=0.61''$

#### NASCRAC

CLOSURE  $K_{MAX}=83.22 \text{ KSI} \sqrt{\text{IN}}$  @ 43,516 CYCLES  $a=0.655''$   
NO CLOSURE SAME AS CLOSURE

### FOURTH CASE R=-0.5

#### NASGRO

CLOSURE  $K_{MAX}=80.00 \text{ KSI} \sqrt{\text{IN}}$  @ 8757 CYCLES  $a=0.61''$   
NO CLOSURE  $K_{MAX}=80.00 \text{ KSI} \sqrt{\text{IN}}$  @ 4010 CYCLES  $a=0.61''$

#### NASCRAC

CLOSURE  $K_{MAX}=83.22 \text{ KSI} \sqrt{\text{IN}}$  @ 3985  $a=0.655''$   
NO CLOSURE SAME AS CLOSURE

# **THROUGH EDGE CRACK CONTINUED** **BENDING ONLY**

## **FIRST CASE R=0**

### **NASGRO**

**$K_{MAX}=80.09 \text{ Ksi}\sqrt{\text{in}}$  @ 10,830 CYCLES a =0.73 in.**

### **NASCRACT**

**$K_{MAX}=81.363 \text{ Ksi}\sqrt{\text{in}}$  @ 10,228 CYCLES a =0.721 in.**

## **SECOND CASE R=-1**

### **NASGRO**

**CLOSURE:  $K_{MAX}=80.03 \text{ Ksi}\sqrt{\text{in}}$  @ 8846 CYCLES a =0.73 in.**



**NO CLOSURE:  $K_{MAX}=80.03 \text{ Ksi}\sqrt{\text{in}}$  @ 2405 CYCLES a =0.73 in.**

### **NASCRACT**

**CLOSURE:  $K_{MAX}=81.36 \text{ Ksi}\sqrt{\text{in}}$  @ 2271 CYCLES a =.721 in.**

**NO CLOSURE: SAME AS CLOSURE**

# THROUGH CRACK AT PIN LOADED HOLE



$w = 1.75"$   
 $t = 0.44"$   
 HOLE DIAMETER = 0.375"  
 EDGE DISTANCE = 0.83"  
 4340 STEEL  
 $\sigma_T = 59 \text{ KSI} + \sigma_{\text{bear}} = 37 \text{ KSI}$   
 CRACK LENGTH = 0.05"  
 $R = 0$

NASGRO MODEL TYPE TC03    NASCRAC MODEL TYPE 208


NASGRO

$$K_{\text{MAX}} = 90.17 \text{ KSI} \sqrt{\text{IN}} @ 4,334 \text{ CYCLES } a_f = 0.339"$$

NASCRAC

$$K_{\text{MAX}} = 90.13 \text{ KSI} \sqrt{\text{IN}} @ 6609 \text{ CYCLES } a_f = 0.492"$$

# THROUGH CRACK AT LUG



NASGRO MODEL TYPE TC04    NASCRAC MODEL TYPE 209

WIDTH = 5.0"  
THICKNESS = 0.25"  
4130 STEEL  
DIAMETER OF HOLE 0.5"  
 $a_i = 0.25"$   
 $\sigma = 150\text{KSI}$

## NASGRO RESULTS

$K_{MAX} = 80.71 \text{ KSI} \sqrt{\text{IN}}$  @ 64,426 CYCLES  $a_f = 1.99"$

## NASCRAC RESULTS

$K_{MAX} = 80 \text{ KSI} \sqrt{\text{IN}}$  @ 113,649 CYCLES  $a_f = 2.184"$

# WALKER CONSTANTS FOR PART THROUGH CENTER CRACK ANALYSIS

MATERIAL: PH 13 - 8 M<sub>0</sub>

TEST CASE NO. 5576

$c$        $7.63 \times 10^{-11}$     IN/CYCLE

$m$       1.0

$n$       3.54

$\Delta K_{th}$       8 KSI $\sqrt{\text{IN}}$

$K_{Ic}$       100 KSI $\sqrt{\text{IN}}$

MATERIAL: TI - 6AL - 4V

TEST CASE NO. 62


$c$        $2.914 \times 10^{-12}$     IN/CYCLE

$m$       0.04435

$n$       4.51


$\Delta K_{th}$       4.5 KSI $\sqrt{\text{IN}}$

$K_{Ic}$       70 KSI $\sqrt{\text{IN}}$



# NASA/FLAGRO PART THROUGH CRACK ANALYSIS

DATA FROM "NASGRO #5576"




TRANSITION TO 1-D SOLUTION TC01 AT 43,531 CYCLES

$a=0.5$ "  $t=0.5$ "  $c=0.62$ "

FAILURE OCCURED AT 43,843 CYCLES  $K_{max} = 100.3 \text{ KSI} \sqrt{\text{IN}}$   $c=0.798$ "

# NASCRAC PART THROUGH CRACK ANALYSIS

DATA FROM "NASCRAC #5576"




TRANSITION TO 202 MODEL AT 45,148 CYCLES

$a=0.5''$   $t=0.5''$   $c=0.702''$


FAILURE OCCURED AT 46,393 CYCLES  $K_{max}=100$  KSI  $\sqrt{IN}$   $c=0.827''$



TEST NO. 62 SPECIMEN NO. 40-8  
 SURFACE FLAW - DEEP -  $a/2c_l \approx 1/2$   
 TI - 6AL - 4V TITANIUM PLATE  
 CONSTANT AMPLITUDE MAX STRESS  $\approx 84$  Ksi,  
 $R \approx +.05$   
 DRY AIR ENVIRONMENT AT 60 CPM  
 TEST LIFE 6784 CYCLES




DEPTH  $a$  OR HALF LENGTH  $c$



# NASA/FLAGRO PART THROUGH CRACK ANALYSIS


DATA FROM "NASGRO #62"



FAILURE OCCURED AT 7855 CYCLES a=0.358" c=0.4" Kmax=85.09 KSI  $\sqrt{\text{IN}}$

# NASCRAC PART THROUGH CRACK ANALYSIS

DATA FROM "NASCRAC TEST 62"



FAILURE OCCURRED AT 7214 CYCLES

$$K_{MAX} = 71 \text{ KSI} \sqrt{\text{IN}} = 0.367$$

## OBSERVATIONS

NASCRAC and NASA/FLAGRO are both user-friendly fracture mechanics analysis codes. Both programs offer a wide variety of crack geometries. Material property data can be read in from a resident file or from user defined input. Load spectra data for the constant amplitude loading cases were utilized easily in both programs.

For the through-crack comparison analysis the Modified Forman equation was used and for the part-through crack analysis the Walker growth rate equation was used.

For the through-crack analysis with an R ratio of zero, results showed good correlation between the two codes except for the through-crack at a lug solution. For  $R = -1, +0.5, -0.5$ , NASA/FLAGRO calculates an m value that is not readily known to the user; it must be hand calculated for use in NASCRAC. By specifying the nonclosure option, m is automatically set to zero. The nonclosure option gave the most conservative results in NASA/FLAGRO. For  $R = -1, +0.5, -0.5$ , changing the m value in NASCRAC had no effect on the results, the m value has been permanently set to some prescribed value. The NASCRAC results for the through-crack analysis for  $R = -1, +0.5, -0.5$  were in the range of the NASA/FLAGRO results for the nonclosure option.

For the part through center crack analysis, both programs gave comparable results, particularly with specimen No. 15576 where the crack grew through before failing, but both programs showed failure before breakthrough for specimen No. 62 which was different from the results of the test.

The comparison analysis between the two programs is an on-going effort for our analysis team. Other types of solution methods and problems are scheduled to be studied in the future.

## REFERENCES

1. NASA/FLAGRO — Fatigue Crack Growth Program, JSC-22267, Johnson Space Center, August 1986.
2. NASCRAC — NASA Crack Analysis Code, Version 1.02, Failure Analysis Associates, April 1988.
3. MSFC-HDBK-1453 — Fracture Control Program Requirements, Marshall Space Flight Center, October 1987.
4. MSFC-STD-1249 — Standard NDE Guidelines and Requirements for Fracture Control Programs, Marshall Space Flight Center, September 11, 1983.
5. NASA CR-134758 — Fracture Control Method for Composite Tanks with Load Sharing Liners, W.D. Bixter, Boeing Aerospace Co., July 1975.
6. Rocketdyne Memorandum 88 RC03594 — Part-Through Crack Growth Test Data, Dale Russell and Bob Primas, Rockwell International Corp., March 17, 1988.
7. MSFC Memorandum ED25(88-35) — Fracture Toughness Properties Used in NASA/FLAGRO, March 7, 1988.

## APPROVAL

### COMPARISON OF TWO COMPUTER CODES FOR CRACK GROWTH ANALYSIS — NASCRAC VERSUS NASA/FLAGRO

By R. Stallworth, C.A. Meyers, and H.C. Stinson

The information in this report has been reviewed for technical content. Review of any information concerning Department of Defense or nuclear energy activities or programs has been made by the MSFC Security Classification Officer. This report, in its entirety, has been determined to be unclassified.



---

JAMES C. BLAIR

Director, Structures and Dynamics Laboratory